



TUF-TOP COATINGS

SINCE 1938

PAVER SEALER 335

ACRYLIC CLEAR FINISH
SOLVENT BASED

DESCRIPTION:

TUF-TOP PAVER SEALER is a high solids, low viscosity, Solvent based, 100 % acrylic, non-yellowing “clear” coating for glazing and sealing bare and colored cement, concrete walks, concrete pavers, and masonry. PAVER SEALER 335 gives a medium to high gloss “wet” look that will withstand mild chemicals, grease, oil, and pick up from hot tires. PAVER SEALER is formulated to be a maintainable finish, and may be easily re-applied to maintain wear areas and increase the overall life expectancy of the coating.

USES:

CONCRETE PAVERS

PATIOS & WALKWAYS

CONCRETE CLEAR SEALER

PREPARATION:

(CONCRETE “PAVER” FINISH COAT)- Please refer to the ICPI Tech Spec #5, to determine the correct cleaning procedures and product choice for sealing pavers in variable environments. Available at www.icpi.org, or contact your local ICPI chapter.

For new pavers no preparation is necessary other than removing any dirt, efflorescence, or sand. For older pavers the surface must be free from dirt, grease and mildew. Scrub with detergent or treat with bleach as needed and rinse thoroughly. If the pavers have been previously sealed, special caution must be taken to insure that PAVER SEALER 335 will adhere to the old sealer. PAVER SEALER 335 will adhere to most solvent based acrylic sealers, but may not adhere to polyurethane or silicate type sealers. Contact the previous installer to find out what type of sealer was used or try a test area. Call your dealer or TUF-TOP for help if uncertain.

(BARE CONCRETE DRIVEWAYS & WALKS)- Concrete should be clean, dry, and free from grease, oil and previous coatings. Pressure washing is recommended. Will adhere over most acrylic sealers . A test patch is recommended to check for adhesion or incompatibility.

(SPRAY DECK)- For newly applied spray deck, no preparation is necessary other than removing any dirt, efflorescence and loose material. The surface must be completely dry, and have a pH. of 10.5 or less or “blushing” / poor adhesion may occur.

PAVER SEALER 335 may be tinted with up to 2 fl. oz per gallon with Industrial tints to achieve an antique or highlighted effect.

APPLICATION:

DO NOT APPLY if rain or heavy dew are forecast within 24 hours of application. Moisture will cause coating to “blush” if not fully cured before exposure. Low temperatures and or high humidity will lengthen cure time.

APPLY in thin coats, allowing at least 2 hours between coats with no more than 4 coats in a 24 hour period to guard against solvent trapping. Do not over apply, blushing, crazing, dirt pick-up and tire printing may result.

(CONCRETE “PAVER” FINISH COAT)- Apply with roller, brush, airless, conventional spray equipment. For most applications, two coats are preferred. Apply first coat, allow to dry a minimum of 6 hours depending on weather, and apply second coat. For best results do not dilute. Allow overnight drying for light foot traffic and 48-72 hours before driving on.